

GRUNDWERTE DER THERMOSPANNUNG IN mV

Temperatur t 90/°C	Typ K	Typ L	Typ J	Typ U	Typ T	Typ E	Typ N	Typ S	Typ R	Typ B
	+NiCr -Ni	+Fe -CuNi	+Fe -CuNi	+ECu -CuNi	+ECu -CuNi	+NiCr -CuNi	+NiCrSi -NiSi	+PtRh 10 -Pt	+PtRh 13 -Pt	+PtRh 30 -PtRh 6
	DIN EN 60584	¹⁾ DIN 43710	DIN EN 60584	¹⁾ DIN 43710	DIN EN 60584	DIN EN 60584	DIN EN 60584	DIN EN 60584	DIN EN 60584	DIN EN 60584
-100	-3,554	-4,75	-4,633	-3,40	-3,379	-5,237	-2,407	-	-	-
0	0	0	0	0	0	0	0	0	0	0
100	4,096	5,37	5,269	4,25	4,279	6,319	2,774	0,646	0,647	0,033
200	8,138	10,95	10,779	9,20	9,288	13,421	5,913	1,441	1,469	0,178
300	12,209	16,56	16,327	14,90	14,862	21,036	9,341	2,323	2,401	0,431
400	16,397	22,16	21,848	21,00	20,872	28,946	12,974	3,259	3,408	0,787
500	20,644	27,85	27,393	27,41	-	37,005	16,748	4,233	4,471	1,242
600	24,905	33,67	33,102	34,31	-	45,093	20,613	5,239	5,583	1,972
700	29,129	39,72	39,132	-	-	53,112	24,527	6,275	6,743	2,431
800	33,275	46,22	-	-	-	61,017	28,455	7,345	7,950	3,154
900	37,326	53,14	-	-	-	68,787	32,371	8,449	9,205	3,957
1000	41,276	-	-	-	-	76,373	36,256	9,587	10,506	4,834
1100	45,119	-	-	-	-	-	40,087	10,757	11,850	5,780
1200	48,838	-	-	-	-	-	43,846	11,951	13,228	6,786
1250	50,644	-	-	-	-	-	45,694	12,554	13,926	7,311
1300	52,410	-	-	-	-	-	47,513	13,159	14,629	7,848
1400	-	-	-	-	-	-	-	14,373	16,040	8,956
1450	-	-	-	-	-	-	-	14,978	16,746	9,524
1500	-	-	-	-	-	-	-	-	-	10,099
1600	-	-	-	-	-	-	-	-	-	11,263
1700	-	-	-	-	-	-	-	-	-	12,433

¹⁾ die DIN-Norm 43710 ist seit 04/94 nicht mehr gültig

Thermospannung in mV, bezogen auf eine Vergleichsstellentemperatur von 0°C